



SUBJECT Chemical Test

TEST LOCATION TÜV SÜD China
TÜV SÜD Products Testing (Shanghai) Co., Ltd.
B-3/4, No.1999 Du Hui Road, Minhang District
Shanghai 201108, P.R. China

CLIENT NAME HANGZHOU FREETRON INDUSTRIAL CO.,Ltd

CLIENT ADDRESS Chunjiang Road No 1117, Economic Development Area of Tonglu, Zhejiang, China

TEST PERIOD 09-Nov-2022~15-Nov-2022

RESULT SUMMARY The tested items **complied with** European COMMISSION REGULATION (EU) No 2020/1245, (EU) No 10/2011 and its amendments on plastic materials and articles intended to come into contact with food.
- Overall migration test **PASS**

Prepared By


Judy hu

(Judy Hu)
Report Drafter

Authorized By

Leo liu

(Leo Liu)
Authorized Signatory



Note: (1) General Terms & Conditions as mentioned overleaf. (2) The results relate only to the items tested.(3) The test report shall not be reproduced except in full without the written approval of the laboratory.(4) Without the agreement of the laboratory, the client is not authorized to use the test results for unapproved propaganda.




SAMPLE SOURCE/ RECEIPT DATE / TEST DATE

Express Logistics/ 09-Nov-2022/ 09-Nov-2022

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED

BY/ ON BEHALF OF THE CLIENTS AS

Sample Name: HP500N
Sample Specification: PP
Batch No./Date: /
Manufacturer: /

SAMPLE NO.	DESCRIPTION	PHOTOGRAPH
721675592-1	Transparent plastic	

TEST RESULT(S)

Note: The migration results in this report were tested and expressed based on repeated use articles.

- Overall Migration Test
 - Test method: With reference to EN 1186-3:2002.
 - Migration ratio(S/V): 5.68dm²/1800ml

Simulant (s) Used	Test Condition	Result(s) [mg/dm ²]			Maximum Permissible Limit [mg/dm ²]
		1 st migration	2 nd migration	3 rd migration	
3% Acetic acid	40°C for 10 days	<3.00	<3.00	<3.00	10
Stability: Comply					

Note: This report is for internal use only such as internal scientific research ,education, quality control, product R&D.

-END OF THE TEST REPORT-